# **Botron B8511 Technical Data Sheet**



#### **Overview:**

Botron's ESD safe paper is uniquely formulated to reduce particulation and smudging. Ideal for controlled environments such as clean rooms and other static free zones. Lays flat and works great in mechanical printing machines.

### PROPERTIES


#### **SPECIFICATIONS**

| Material:               |                             |
|-------------------------|-----------------------------|
| Color:                  | Blue, White and Green       |
| Sheet Size:             | 8.5" x 11"                  |
| Packaging:              | 250 sheets/Rm - 10Rms/Cs    |
| Basis Weight:           | #/3000 ft^2 23lbs /80 g/m^2 |
| Caliper / mils:         | 4.7                         |
| Tear (g) MD:            | 104                         |
| Internal Bond (oz/in):  | 13.1                        |
| Porosity (seconds):     | 5                           |
| Extractable IONS (ppm): |                             |
| Chloride:               | 136                         |
| Potassium:              | 60.3                        |
| Sodium:                 | 284                         |
| Non Volatile Residue    |                             |
| (g/m^2):                |                             |
| DI Water:               | .31                         |
| Isopropyl Alcohol:      | .63                         |
| Freon TF:               | .32                         |
|                         |                             |
| .C.P. Analysis P.P.B.:  |                             |
|                         |                             |

Li Na Mg Ai K Ca Cr Fe Ni Cu Zn Ag <0.001 35.410 1.546 .0.064 8.445 7.897 <0.001 0.052 0.006 0.008 0.016<0.001 Particle Generation: Per IES-RP-CC004.2, Sec 6.2 Particles (>0.5um)

## PART NUMBERS

B8511 ESD Safe Paper



- High Tear and Tensile Strength
- Ultra Low Particulation
- 500 Page Ream
- Burst Strength 50lbs
  per Inch



#### Botron Company Inc. | 325 W. Melinda Ln Phoenix AZ 85027 | Ph# 623-582-6700 | Fax# 623-582-6776

**Disclaimer.** All statements of technical information are believed to be true and are based upon tests we believe to be reliable. The proper use and application for this product must be the responsibility of the user. The statements herein shall have no force or effect.